



*CHS41 is a dual wall adhesive lined heatshrink tubing manufactured from flame retardant cross-linked polyolefin. This tubing may be used in a wide variety of electrical applications and provides excellent waterproofing and moisture protection. Its high shrink ratio makes it ideal for sealing irregular shapes.*

This product has the certifications below:



Colours Available:

■ Black

Material Specification:

Material: Polyolefin

Shrink Ratio: 4:1

Operating Temperature Range: -55°C to +125°C

Flammability: VW-1

RoHS and REACH compliant

**C TIE**

Unit 5, Axiom Business Park,  
41 Balcombe Road, Horley, Surrey, RH6 7HF  
Tel: 01737 760645 Fax: 01737 760946  
E-mail: sales@ctie.co.uk

Property	Specification Requirement	Test Method	Typical Result
Longitudinal Shrinkage	<10%	ASTM D 2671	<5%
Tensile Strength	10.4 MPa min	ASTM D 638	>12 MPa
Elongation at break	200% min	ASTM D 638	>400%
Tensile strength after ageing (175oC, 168hrs)	7.28 MPa min	ASTM D 638	>10.4 MPa
Elongation after ageing (175oC, 168hrs)	100% min	ASTM D 638	>300%
Heat shock (250oC, 4hrs)	No Crack	ASTM D 2671	No Crack
Low temperature flexibility (-55oC, 4hrs)	No Crack	ASTM D 2671	No Crack
Dielectric voltage withstand	2500V, 60 sec, no breakdown	ASTM D 2671	No Breakdown
Dielectric Strength	19.7 KV/mm min	ASTM S 2671	>25 KV/mm
Volume resistivity	10 <sup>14</sup> Ω cm min	ASTM D 876	>10 <sup>14</sup> Ω cm
Corrosion	No Corrosion	ASTM D 2671	No Corrosion
Flammability	VW-1	UL224	Pass

**C TIE**

Unit 5, Axiom Business Park,  
 41 Balcombe Road, Horley, Surrey, RH6 7HF  
 Tel: 01737 760645 Fax: 01737 760946  
 E-mail: sales@ctie.co.uk

All Specifications  
 are Subject to  
 change